

RI

bureau of mines
report of investigations 7400

Property of
MSHA INFORMATIONAL SERVICE

COAL CARBONIZATION STUDIES

Altering Composition and Yield
of Volatile Products by Increasing
the Free Space Above the Charge



UNITED STATES DEPARTMENT OF THE INTERIOR

BUREAU OF MINES

June 1970

COAL CARBONIZATION STUDIES

Altering Composition and Yield
of Volatile Products by Increasing
the Free Space Above the Charge

By C. Ortuglio, J. G. Walters, and D. E. Wolfson

* * * * * report of investigations 7400



UNITED STATES DEPARTMENT OF THE INTERIOR

BUREAU OF MINES

This publication has been cataloged as follows:

Ortuglio, Carmen

Coal carbonization studies: altering composition and yield of volatile products by increasing the free space above the charge, by C. Ortuglio, J. G. Walters, and D. E. Wolfson. [Washington] U.S. Dept. of the Interior, Bureau of Mines [1970]

11 p. tables. (U.S. Bureau of Mines. Report of investigations 7400)

Includes bibliography.

1. Coal--Carbonization. I. Walters, Jack G., jt. auth. II. Wolfson, David E., jt. auth. III. Title. (Series)

TN23.U7 no. 7400 622.06173

U.S. Dept. of the Int. Library

CONTENTS

	<u>Page</u>
Abstract.....	1
Introduction.....	1
Experimental procedures.....	2
Properties of tar.....	4
Properties of gas.....	7
Light oil.....	8
Properties of coke.....	9
Conclusions.....	9
References.....	11

TABLES

1. Retort test condition.....	2
2. Chemical analyses of coals, as-carbonized.....	3
3. Screen size of coal, as-carbonized.....	3
4. Yield of carbonization products, as-carbonized basis.....	4
5. Yield of carbonization products, moisture- and ash-free basis.....	4
6. Specific gravity and component tar yields.....	5
7. Effect of free space on the chemical composition of tar and pitch...	6
8. Effect of free space above coal charge on quinoline and benzene insolubles.....	6
9. Chemical and physical properties of gas.....	7
10. Composition of light oil.....	8
11. Physical properties of coke.....	9

COAL CARBONIZATION STUDIES

Altering Composition and Yield of Volatile Products by Increasing the Free Space Above the Charge

by

C. Ortuglio,¹ J. G. Walters,² and D. E. Wolfson²

ABSTRACT

The effect of cracking by increasing the free space above the charge on the composition and yields of the volatile products from carbonization of Pittsburgh-bed coal and one industrially used blend from Eastern United States and one from Western United States was investigated with the BM-AGA carbonization apparatus. Increasing the free space above the charge from 1 inch to 3 inches, to 6 inches, and to 9 inches resulted in lower tar yields and increased gas and light oil yields. Anthracene and naphthalene yields were increased; quinoline and benzene insoluble fractions of both the tar and pitch increased considerably with increased free space, although the carbon content of the tars and pitches increased only slightly. Increased cracking, occasioned by the increase in free space, resulted in a decrease in the yields of tar acids, tar bases, neutral oils, olefins, aromatics, and paraffins and naphthenes. Gas composition was relatively constant; hydrogen and methane tended to increase and ethane decrease. Results of the investigation are being used to design a unit to upgrade the volatile products of carbonization by cracking the hot products as they leave the carbonization chamber.

INTRODUCTION

The Bureau of Mines, in cooperation with the American Gas Association, jointly developed a pilot-scale carbonization test apparatus (BM-AGA) to determine the carbonization characteristics of coals and to evaluate the byproduct yields (6).³ Although the BM-AGA test apparatus is used primarily to determine the coking characteristics of coals for metallurgical use, the objective of this investigation was to determine the effect of cracking on the quality of carbonization products by varying the free space above the coal charge when the temperature is kept constant. It was realized that the test method used would be economically infeasible commercially because of reduced coke

¹Research chemist.

²Engineer-in-charge, Coal Carbonization.

All authors are with the Pittsburgh Coal Research Center, Bureau of Mines, Pittsburgh, Pa.

³Underlined numbers in parentheses refer to items in the list of references at the end of this report.

production; however, the tests were made to obtain data to determine if the tar vapors were sufficiently altered to justify further investigations of the carbonization variables which affect yield and composition of the byproducts.

Carbonization yields are influenced by the rank of coal carbonized, whereas their composition is primarily a function of the temperature and contact time of the evolved vapors with the heated surfaces within the retort or ovens. Decomposition of vapors proceeds in two steps: Primary decomposition of gaseous vapors as they are evolved from the plastic layer at moderate temperatures and then pass through the hot coke surfaces, and secondary decomposition as the vapors pass through the free space above the coal charge with less contact surface. Porter (5) in a study of coal carbonizing equipment has found that the variability of contact time of the gases and vapors passing through the heated spaces in approved industrial ovens may be 100 percent or more.

EXPERIMENTAL PROCEDURES

Procedure and apparatus for BM-AGA carbonization tests have been described in detail in a previous publication (6). Basically, the apparatus consists of a cylindrical steel retort, electrically controlled resistance type furnace, product recovery train, gas scrubbers, meters, and sampler. The standard retort used throughout this investigation is 26 inches high and 18 inches in diameter. The results from previous carbonization tests, using standard retorts and 900° C carbonization temperatures, have been correlated with industrial (7) and experimental oven (3, 8) data. The coal charges were adjusted in height so as to leave 1, 3, 6, and 9 inches of free space above the coal charge. Duplicate carbonization tests were made at 900° C and the results reported are averages of two determinations.

A single coal (1166) and two commercial coal blends (1161 and 1167-A) were used in this investigation. Table 1 shows the retort test condition and charge bulk density, and tables 2 and 3 present the chemical analyses, miscellaneous properties, and screen size test of the coals, as-carbonized. Coal 1161 was carbonized as received so that the size consist would be comparable to that charged at the coke plant. Coals for tests 1166 and 1167-A were received separately in lump form and were crushed in the hammer mill and blended.

TABLE 1. - Retort test condition

Free space, inches	Free space, percent	Volume of charge, cubic feet	Volume of free space, cubic feet
0	0	3.829	0
1	3.8	3.682	0.147
3	11.5	3.387	.442
6	23.1	2.945	.884
9	34.6	2.503	1.326

TABLE 2. - Chemical analyses of coals, as-carbonized

Coal number.....	1161	1166	1167-A
Dry, mineral-matter-free fixed carbon, percent.....	62.0	59.0	65.2
Moist, mineral-matter-free heating value, Btu.....	14,140	14,700	14,970
Proximate analysis, percent:			
Moisture.....	7.4	3.9	3.2
Volatile matter.....	33.0	37.3	32.0
Fixed carbon.....	52.7	52.5	58.5
Ash.....	6.9	6.3	6.3
Ultimate analysis, percent:			
Hydrogen.....	5.7	5.5	5.2
Carbon.....	73.7	76.0	78.5
Nitrogen.....	1.5	1.5	1.5
Oxygen.....	11.6	9.1	7.1
Sulfur.....	.6	1.6	1.4
Ash.....	6.9	6.3	6.3
Softening temperature of ash, ° F.....	2,320	2,500	2,280
Free swelling index.....	7½	8	7½
Agglutinating value.....	5.9	9.6	8.3

TABLE 3. - Screen size of coal, as-carbonized¹

Coal number.....	1161	1166	1167-A
Size fraction, weight-percent:			
Plus 4 mesh.....	15.9	4.3	1.4
Minus 4 plus 8 mesh.....	18.0	24.3	18.5
Minus 8 plus 14 mesh.....	16.5	24.6	26.5
Minus 14 plus 35 mesh.....	23.3	24.8	27.6
Minus 35 plus 80 mesh.....	15.3	10.1	12.1
Minus 80 plus 150 mesh.....	3.8	4.5	4.8
Minus 150 plus 200 mesh.....	1.5	3.0	1.2
Minus 200 mesh.....	5.7	4.4	7.9

¹Tyler series.

In computing yields from BM-AGA carbonization tests, the quantitative yields are based on U.S. gallons (231 cubic inches) and short tons (2,000 pounds). Coke yields are reported as dry coke, weight-percent of coal carbonized. The yield, specific gravity (determined), and gross heating value of the gas are reported as stripped of light oil and saturated water vapor at 60° F and under a pressure equivalent to 30 inches of mercury. Light oil refers to the crude product stripped from the gas. Liquor includes the fixed ammonia and absorbed free ammonia. Ammonium sulfate is reported in pounds per ton of coal and includes the total free and fixed ammonia. The tar yield, properties, and constituents are reported on a dry basis and includes only that light oil which condenses with the tar, and the specific gravity of the tar is reported at 15.5° C/15.5° C.

The yields of carbonization products are given on the as-carbonized basis (table 4) and on the moisture- and ash-free basis (table 5). The latter basis is used to compare coals when the moisture and ash contents differ

significantly. Comparisons lose their significance because a high percentage of ash or moisture makes the yield of coke or liquor artificially high and those of other products correspondingly low. The calculation of moisture- and ash-free basis assumes that all ash remains in the coke and that all moisture in the coal is recovered as liquor.

TABLE 4. - Yield of carbonization products, as-carbonized basis

Coal number	Free space, inches	Yields, weight-percent							Yields per ton of coal			
		Coke	Gas	Tar	Light oil	Liquor	Free ammonia	Total	Gas, cubic feet	Tar, gallons	Light oil in gas, gallons	Ammonium sulfate, pounds
1161	1	65.9	18.2	5.8	1.13	8.8	0.160	100.0	10,450	11.9	2.81	21.3
	3	65.6	16.5	5.5	1.17	10.2	.177	99.1	10,640	11.2	3.25	23.6
	6	65.7	16.2	5.5	1.23	10.3	.180	99.1	10,770	11.1	3.42	22.8
	9	65.5	16.3	5.3	1.13	10.0	.209	98.4	10,790	10.2	3.16	23.1
1166	1	66.3	14.9	7.6	1.28	8.8	.166	99.0	10,400	15.8	3.57	25.3
	3	66.3	15.3	8.1	1.24	8.0	.168	99.1	10,750	16.5	3.45	23.7
	6	66.4	15.3	7.7	1.31	7.6	.173	98.5	10,700	15.2	3.64	22.6
	9	66.4	15.2	7.5	1.37	7.7	.174	98.3	10,850	14.8	3.81	22.1
1167-A	1	70.8	13.6	6.7	1.16	7.0	.163	99.4	10,140	13.7	3.23	23.2
	3	70.7	13.9	6.4	1.15	6.2	.161	98.5	10,290	12.9	3.20	20.8
	6	70.7	13.9	6.2	1.24	6.1	.164	98.3	10,350	12.1	3.47	20.0
	9	70.7	14.1	6.1	1.21	6.3	.149	98.6	10,490	11.9	3.36	18.8

TABLE 5. - Yield of carbonization products, moisture- and ash-free basis

Coal number	Free space, inches	Yields, weight-percent							Yields per ton of coal			
		Coke	Gas	Tar	Light oil	Liquor	Free ammonia	Total	Gas, cubic feet	Tar, gallons	Light oil in gas, gallons	Ammonium sulfate, pounds
1161	1	68.8	21.2	6.7	1.32	1.6	0.187	99.8	12,190	13.9	3.27	24.9
	3	68.5	19.3	6.4	1.37	3.3	.207	99.1	12,420	13.1	3.79	27.5
	6	68.6	18.9	6.4	1.44	3.4	.210	99.0	12,570	13.0	3.99	26.6
	9	68.4	19.0	6.2	1.32	3.0	.244	98.2	12,590	11.9	3.69	27.0
1166	1	66.8	16.6	8.5	1.43	5.5	.185	99.0	11,580	17.6	3.98	28.2
	3	66.8	17.0	9.0	1.38	4.7	.187	99.1	11,970	18.4	3.84	26.4
	6	66.9	17.0	8.6	1.46	4.1	.193	98.3	11,920	16.9	4.05	25.2
	9	66.9	16.9	8.4	1.53	4.2	.194	98.1	12,080	16.5	4.24	24.6
1167-A	1	71.3	15.0	7.4	1.28	4.2	.180	99.4	11,200	15.1	3.57	25.6
	3	71.2	15.4	7.1	1.27	3.3	.178	98.4	11,370	14.3	2.21	23.0
	6	71.2	15.4	6.9	1.37	3.2	.181	98.3	11,440	13.4	3.83	22.1
	9	71.2	15.6	6.7	1.34	3.4	.165	98.7	11,590	13.1	3.71	20.8

Properties of Tar

The tar yields are affected by coal rank, temperature of carbonization, and free space above the coal charge. The temperature of carbonization is the most significant contributing factor in determining tar quality. Increased free space permits the vapors to remain longer at the higher temperatures resulting in considerable variations in tar quality.

The effect of free space on tar quality is presented in table 6. Cracking of tar due to increased free space resulted in progressive increases in its specific gravity, naphthalene yield, and anthracene yield (except for the 9-inch free space) and a reduction in tar acids, bases, and neutral oils. It is interesting to note that unlike naphthalene, the anthracene yield was slightly less at the 9-inch free space for all tests. There was no significant change in the residue yield.

TABLE 6. - Specific gravity and component tar yields

Coal number	Void space, inches	Specific gravity of tar	Yields, gallons per ton							Yields, pounds per ton	
			Acids	Bases	Neutral oils	Residue	Neutral oils			Naphthalene	Anthracene
							Olefins	Aromatics	Paraffins and naphthenes		
1161	1	1.17	0.52	0.33	3.50	6.82	0.39	2.95	0.16	5.36	2.81
	3	1.19	.35	.27	2.89	6.60	.31	2.52	.06	7.42	3.58
	6	1.20	.20	.22	2.31	7.10	.25	2.04	.02	8.70	5.25
	9	1.23	.11	.15	1.63	7.03	.17	1.45	<.01	9.55	4.71
1166	1	1.16	.78	.32	3.95	10.26	.33	3.52	.10	3.57	1.36
	3	1.18	.55	.28	3.69	10.87	.32	3.33	.04	7.20	2.34
	6	1.20	.25	.24	2.57	10.89	.29	2.26	.02	10.32	3.27
	9	1.21	.20	.22	2.20	10.86	.24	1.95	.01	11.59	2.52
1167-A	1	1.17	.69	.27	3.50	8.68	.31	3.14	.09	4.14	1.92
	3	1.19	.37	.26	2.41	8.82	.20	2.19	.03	7.53	3.12
	6	1.22	.21	.18	1.98	8.54	.21	1.76	.01	8.97	3.31
	9	1.22	.17	.17	1.78	8.57	.21	1.57	.01	9.92	2.95

The chemical composition of tars and pitches is presented in table 7. As expected, the carbon content increased and the hydrogen content decreased with progressive increases in the free space.

Quinoline-insoluble (1) and benzene-insoluble (free carbon) (6) values for the tars and pitches, as well as the softening point of the pitches, were determined. These are critical factors, commercially important, in determining the suitability of coal tar pitches as electrode binders. The tar values were determined on the whole tar and the pitch values were determined on the +350° C fraction of the tar. The cube-in-air method (1, p. 705) was used to determine the softening point of the pitches. The results are presented in table 8.

The insolubility values for all tars and pitches increased with increasing free space. There were marked increases at the 9-inch free space for all tests, indicating the formation of insoluble high boiling hydrocarbons.

TABLE 7. - Effect of free space on the chemical composition of tar and pitch, percent

Void space, inches	Tar				Pitch			
	1	3	6	9	1	3	6	9
COAL 1161								
Hydrogen.....	5.7	5.2	5.0	4.7	4.8	4.4	4.3	3.9
Carbon.....	90.5	91.4	92.7	93.1	92.3	92.8	93.8	94.2
Nitrogen.....	1.1	1.2	1.1	1.0	1.4	1.3	1.2	1.0
Oxygen.....	2.2	1.7	.7	.7	1.1	1.1	.3	.4
Sulfur.....	.4	.4	.4	.4	.3	.3	.3	.3
Ash.....	.1	.1	.1	.1	.1	.1	.1	.2
COAL 1166								
Hydrogen.....	5.4	5.0	4.8	4.7	4.9	4.7	4.6	4.2
Carbon.....	89.7	90.4	90.8	91.1	90.5	91.0	91.9	92.1
Nitrogen.....	1.3	1.3	1.2	1.1	1.5	1.4	1.3	1.3
Oxygen.....	2.5	2.2	2.1	2.0	2.1	2.0	1.3	1.6
Sulfur.....	1.0	1.0	1.0	1.0	.8	.7	.7	.7
Ash.....	.1	.1	.1	.1	.2	.2	.2	.1
COAL 1167-A								
Hydrogen.....	5.8	5.4	5.1	5.0	4.9	4.7	4.6	4.4
Carbon.....	90.3	92.0	91.5	92.0	91.1	91.6	92.0	92.2
Nitrogen.....	1.3	1.3	1.3	1.3	1.5	1.4	1.4	1.3
Oxygen.....	1.4	.4	1.0	.6	1.7	1.5	1.2	1.3
Sulfur.....	1.0	.8	1.0	1.0	.7	.7	.7	.7
Ash.....	.2	.1	.1	.1	.1	.1	.1	.1

TABLE 8. - Effect of free space above coal charge on quinoline and benzene insolubles

Coal number	Void space, inches	Tar ¹		Pitch ¹		Softening point, ° C
		Quinoline insolubles	Benzene insolubles	Quinoline insolubles	Benzene insolubles	
1161	1	1.70	6.61	3.85	25.95	119.0
	3	2.73	8.17	3.96	24.25	105.0
	6	4.84	11.29	8.87	28.33	110.0
	9	11.07	17.42	22.03	32.55	138.0
1166	1	2.26	8.64	2.82	22.55	96.8
	3	4.13	11.60	4.78	26.55	101.0
	6	7.29	14.26	9.14	28.33	94.0
	9	11.15	18.76	14.34	30.87	85.8
1167-A	1	2.57	7.66	2.86	21.75	94.0
	3	3.87	10.34	4.73	23.70	94.3
	6	6.39	12.47	7.60	25.15	82.3
	9	9.50	15.46	12.15	27.85	85.0

¹Weight-percent for tar and pitch.

Properties of Gas

Properties of byproduct gas vary with carbonizing conditions as well as with coal characteristics. An investigation (9) of the gas yielded by coals carbonized by the BM-AGA method at 900° C showed that the physical and chemical properties of the gas depend on the rank of coal.

The yield of carbonization gas increases with increased carbonization temperature; similarly, maintaining the effluent vapors at elevated temperatures by increasing the free space above the coal charge exposes the vapors to high temperatures for a longer time, resulting in degradation of the volatile material with a still greater increase in the gas yield. Davis and Auvil (4) have attributed this increase to greater cracking of hydrocarbons in the enlarged free space. Table 5 shows that the gas yield increases with free space and that the greatest variation in gas yield was 500 cubic feet, or 4.3 volume-percent.

The chemical and physical properties of the gas are presented in table 9. Two important properties of gas are its heating value and hydrogen sulfide content. The heating value, generally considered to be the most important property of byproduct gas, is presented on both the cubic-foot and pound-of-coal bases. The greatest heat recovery for the longest exposure time of gas in the retort was 112 Btu per pound of coal (1167-A), or a gain of 224,000 Btu per ton of coal. Coal 1161 showed a steady decline in heating value with increased exposure time.

TABLE 9. - Chemical and physical properties of gas

Coal number	Void space, inches	Specific gravity	Composition, dry, volume-percent					Heating value		Hydrogen sulfide, grains per 100 cu ft
			Hydrogen	Carbon monoxide	Methane	Ethane	Ethylene	Btu per cu ft	Btu per lb coal	
1161	1	0.395	60.87	5.98	25.78	2.43	5.03	618	3,235	131
	3	.387	62.13	6.07	24.51	2.15	5.14	608	3,231	157
	6	.377	64.01	5.07	23.79	1.60	5.53	600	3,180	157
	9	.369	63.29	5.91	27.40	1.08	2.32	576	3,121	165
1166	1	.366	59.38	6.49	30.08	1.42	2.63	603	3,133	638
	3	.361	59.37	6.13	30.11	1.56	2.83	608	3,268	714
	6	.362	59.09	6.45	30.97	.92	2.57	601	3,221	707
	9	.360	61.87	4.52	29.85	.75	2.96	596	3,189	828
1167-A	1	.340	63.91	4.31	28.81	1.30	1.67	583	2,956	561
	3	.340	61.94	5.12	30.05	.85	2.04	587	3,020	600
	6	.339	61.98	5.15	30.08	.70	1.29	581	3,007	606
	9	.339	61.91	4.85	30.94	.56	1.74	585	3,068	644

The hydrogen sulfide content of the gas, calculated to grains per 100 cubic feet of gas, is becoming increasingly important because of air pollution restrictions, and must be reduced to limited concentrations before

disposal. Results indicate that the formation of hydrogen sulfide is related to exposure time; however, the concentration of hydrogen sulfide in the byproduct gas is dependent on the sulfur content of the coal and is not related to coal rank. Although the sulfur content for coal 1167-A (1.4 percent) was higher than that for coal 1161 (0.6 percent), the net increase in hydrogen sulfide, attributed to free-space cracking, was only 14.8 percent, compared with 26.0 percent for coal 1161.

Light Oil

The composition of light oil, like that of the tar, is a function of the carbonizing conditions of which temperature, free space above the coal charge, and the contact time of the gas in the hot free space are the most important; however, the total yield of light oil under normal carbonizing conditions is dependent largely upon the rank of the coal.

Benzene, the principal constituent of the light oil, is a decomposition product whose formation is accelerated under conditions favorable to cracking effluent vapors.

The percentage composition of benzene in the light oil, as presented in table 10, progressively increased with an increase in free space, whereas all other constituents of light oil were adversely affected by the free space increases.

TABLE 10. - Composition of light oil, gallons per ton

Coal number	Void space, inches	Benzene	Toluene	m,p-xylene	o-xylene	Ethylbenzene
1161	1	2.24	0.38	0.12	0.05	0.01
	3	2.65	.42	.14	.04	.006
	6	2.91	.40	.09	.01	.004
	9	2.89	.22	.04	.01	-
1166	1	2.77	.64	.13	.02	.004
	3	2.79	.55	.08	.02	.003
	6	3.13	.45	.05	.01	.001
	9	3.34	.42	.04	.01	.001
1167-A	1	3.05	.06	.10	.02	.013
	3	3.05	.05	.07	.02	.003
	6	3.39	.04	.03	.01	.001
	9	3.30	.03	.03	.01	.001

The total light oil yield reached a maximum at the 6-inch free space for the coal blends and at the 9-inch free space for the straight coal.

Properties of Coke

The physical properties of the cokes presented in table 11 were determined by standard methods of the American Society for Testing Materials (2). The tumbler indices, 1-inch stability and 1/4-inch hardness, are the only coke properties reported as these parameters are most commonly used in evaluating metallurgical coke.

TABLE 11. - Physical properties of coke

Coal number	Void space, inches	ASTM tumbler index	
		1-inch	1/4-inch
1161	1	37	61
	3	37	59
	6	36	58
	9	37	63
1166	1	33	50
	3	31	51
	6	29	49
	9	28	51
1167-A	1	45	61
	3	45	62
	6	42	58
	9	42	59

Variations of free space had no effect on the coke yield. The only significant change in the coking properties was for coal 1166 in which the 1-inch stability index was progressively lowered from 33 for the 1-inch free space to 28 for the 9-inch free space. The stability and hardness indices for both coal blends remained essentially the same.

CONCLUSIONS

The yields of carbonization products are influenced by the rank of coal used and the temperature of carbonization. The primary decomposition is influenced by the rate of heating and the secondary decomposition by the time of contact of the vapors while in the hot retort and is dependent on the volume of free space per unit volume of charge.

The cracking of tar due to increased free space resulted in progressive increases in specific gravity, naphthalene yield, anthracene yield (except for the 9-inch free space test), and a reduction in tar acids, bases, and neutral oils.

Free space increases had no effect on the coke yield or coke properties except for the 1-inch tumbler stability for coal 1166, which was progressively lowered with increased free space.

The light oil yield was increased and reached a maximum at 6-inch free space for the coal blends, and 9-inch free space for the straight coal.

There was a progressive increase in gas yield, with the greatest variation of 500 cubic feet per ton of coal, and the heat recovery for the longest exposure of gas in the retort was 112 Btu per pound of coal.

Increased free space above the coal charge during carbonization permitted longer residence time of the vapors at a specific temperature and improved the quality of the byproducts. However, since coke is the major and most valuable product of coal carbonization, it would be economically infeasible to decrease the capacity of commercial ovens. In recognition of this, the Bureau of Mines is investigating the upgrading of volatile materials, in a separate cracking unit outside of the coking furnace. Results of this investigation will be published in a subsequent report.

REFERENCES

1. American Society for Testing and Materials. Bituminous Materials, Soils, Skid Resistance. Part II, March 1969, pp. 701-705.
2. _____. ASTM Standards on Coal and Coke. 1954, 155 pp.
3. Bureau of Mines. Comparative Evaluation of Coking Properties of Four Coals. BuMines Inf. Cir. 8010, 1961, 22 pp.
4. Davis, J. D., and S. Auvil. High Temperature Carbonization of Coal. Ind. and Eng. Chem., v. 27, April 1935, p. 459.
5. Porter, H. C. Improvement of Design of Coal Carbonization Equipment. Ind. and Eng. Chem., v. 24, 1932, pp. 1363-1368.
6. Reynolds, D. A., and C. R. Holmes. Procedure and Apparatus for Determining Carbonizing Properties of American Coals by the Bureau of Mines-American Gas Association Method. BuMines Tech. Paper 685, 1946, 35 pp.
7. Walters, J. G., and G. W. Birge. Duplicability Studies of the BM-AGA Test Method and Correlation With Industrial Coking. BuMines Rept. of Inv. 5467, 1959, 16 pp.
8. Wolfson, D. E., G. W. Birge, and J. G. Walters. Comparison of Properties of Coke Produced by BM-AGA and Industrial Methods. BuMines Rept. of Inv. 6354, 1964, 19 pp.
9. Wolfson, D. E., and D. A. Reynolds. Yields and Properties of Gases From BM-AGA Carbonization Tests at 900° C. BuMines Tech. Paper 693, 1946, 12 pp.