

United States Patent [19]

Gomes et al.

[11] E

Patent Number: **Re. 32,612**

[45] Reissued Date of Patent: **Feb. 23, 1988**

[54] **FORMATION OF TUNGSTEN MONOCARBIDE FROM A MOLTEN TUNGSTATE-HALIDE PHASE BY GAS SPARGING**

[75] Inventors: **John M. Gomes, Reno; Andrea E. Raddatz, Sparks; Elizabeth G. Baglin, Reno, all of Nev.**

[73] Assignee: **The United States of America as represented by the Secretary of the Interior, Washington, D.C.**

[21] Appl. No.: **855,284**

[22] Filed: **Apr. 24, 1986**

Related U.S. Patent Documents

Reissue of:

[64] Patent No.: **4,489,044**
Issued: **Dec. 18, 1984**
Appl. No.: **574,499**
Filed: **Jan. 27, 1984**

U.S. Applications:

[63] Continuation-in-part of Ser. No. 544,299, Oct. 21, 1983, abandoned.

[51] Int. Cl.⁴ **C01G 41/00**

[52] U.S. Cl. **423/53; 423/440;**

423/DIG. 12

[58] Field of Search **423/53, 440, DIG. 12**

[56]

References Cited

U.S. PATENT DOCUMENTS

3,373,097	3/1968	Gomes et al.	204/64 R
3,482,941	12/1969	Palm	423/440
3,692,479	9/1972	Meadows et al.	423/440
3,902,917	9/1975	Baresel et al.	423/440
4,190,439	2/1980	Gortsema	423/440
4,256,496	3/1981	Brandstatler	423/53

FOREIGN PATENT DOCUMENTS

1190713	5/1970	United Kingdom	423/440
---------	--------	----------------	---------

Primary Examiner—Robert L. Stoll

Attorney, Agent, or Firm—E. Philip Koltos

[57]

ABSTRACT

Tungsten monocarbide is prepared by sparging a molten composition comprising an alkali metal halide and an oxygen compound of tungsten with a gas comprising a gaseous hydrocarbon, particularly methane.

11 Claims, No Drawings

FORMATION OF TUNGSTEN MONOCARBIDE FROM A MOLTEN TUNGSTATE-HALIDE PHASE BY GAS SPARGING

Matter enclosed in heavy brackets [] appears in the original patent but forms no part of this reissue specification; matter printed in italics indicates the additions made by reissue.

This application is a continuation-in-part of pending application Ser. No. 544,299, filed Oct. 21, 1983 *now abandoned*.

This invention relates to a process for preparation of tungsten monocarbide (WC) from oxygen compounds of tungsten.

Recent technological advances have resulted in an ever increasing demand for materials that are capable of delivering constant chemical and physical performances under a variety of extreme operating conditions. For example, the development of supersonic aircraft and rockets is based upon the availability of such materials.

One material of relatively recent importance is tungsten. Tungsten possesses a high melting point and is useful in its elemental form, particularly as an alloy for high-temperature applications. Tungsten is also useful in the form of tungsten monocarbide for use in abrasives and cutting instruments. As the demand for increased availability of such materials has advanced, so has the necessity for improved techniques for their production and recovery.

In the past, recovery of tungsten from its ores was an expensive and relatively complex process involving both physical and chemical separation procedures. Tungsten was usually recovered either from wolframite, $(\text{Fe}, \text{Mn})\text{WO}_4$, or scheelite, CaWO_4 , by various pyrometallurgical and extraction procedures. The carbide final product would then be obtained by reacting the purified metal with carbon in another sequence of reactions.

The predominant commercial process for the preparation of tungsten carbide from wolframite or scheelite concentrates requires many steps because the preparation of high purity tungsten powder is necessary before synthesis of tungsten carbide.

In the commercial production of tungsten monocarbide by direct synthesis, tungsten powder is mixed with 6.2-6.9% carbon. This amount of carbon is 2-10% in excess of the stoichiometric amount in WC (6.13%) and is required to decrease the oxygen content. The mixture is usually blended in a rotary blender containing steel or tungsten carbide balls. Typically one-half of the tungsten powder will be added to all of the carbon, blended for several hours, and this is followed by the addition of the remaining tungsten powder and additional several hours of blending. Careful blending procedures are required, particularly in the case of coarse tungsten powder, because of great disparity in density of the constituents and the size effects of the particles. The tungsten-carbon mixture is next put into graphite boats and passed continuously through a tube furnace. The furnace may be either gas fired or electrically heated, but must be maintained in the temperature range of 1,400° to 1,600° C. Hydrogen is usually introduced into the discharge end of the tube and is burned off at the charging end. The time per furnace cycle is 4 to 5 hours.

The major disadvantage of this process is the requirement for high purity tungsten powder as the feed material for synthesis of the carbide. The complete process for preparing monocarbide from ore concentrates includes the following steps: (1) pressure digestion to decompose the ore, (2) solution purification, (3) solvent extraction, (4) ammonium hydroxide stripping, (5) ammonium paratungstate crystallization, (6) formation of tungsten metal by hydrogen reduction, and (7) carbide synthesis.

Aluminothermic reduction is also used to produce WC from ore concentrates. This process consists of blending the concentrates, aluminum, calcium carbide and other reagents in a tear-down carbon lined refractory furnace. A thermite reaction is started and the whole mass becomes molten, thereby producing a slag and an iron-manganese alloy containing WC crystals. The furnace is cooled in about 10-14 days and the slag and menstruum separated. The menstruum is then crushed and leached to yield a coarse WC product. The coarse WC crystals next are ground in a WC rod or ball mill and yield a commercial WC product.

This technique, however, is also disadvantageous in that it requires a large amount of energy for size reduction and leaching the menstruum, and also for the size reduction of the recovered WC crystals. Additionally, the carbide thus formed is not suitable for preparing many cemented carbide products.

U.S. Pat. No. 3,482,941 to Palm discloses another method for recovering tungsten in the form of tungsten carbide from scheelite by heating ore with silica and carbon. This process is said to reduce the amount of ditungsten carbide which is commonly formed when tungsten carbide is prepared at elevated temperatures.

U.S. Pat. No. 4,256,496 to Brandstatter discloses an additional process for the recovery of metal ores utilizing a solid state reduction and carburization reaction. The disclosed process utilizes physical separation techniques, such as gravity separation employing water elutriation. The separation is based upon the different physical properties of metal carbides and various gangue oxide constituents of ores at elevated temperatures.

It has now been found, according to the present invention, that preparation of tungsten monocarbide from oxygen compounds of the metal may be efficiently and economically accomplished by subjecting a melt of an alkali metal halide and the tungsten compound to sparging with a hydrocarbon gas. The process of the invention has been found to be particularly applicable to preparation of tungsten monocarbide from tungstic oxide or tungstates such as sodium tungstate and ammonium paratungstate.

The preferred alkali metal halide will generally be sodium chloride since it is usually most readily available and economical. However, the alkali metal halide may also consist of fluorides or bromides of sodium, potassium, or lithium. In addition, mixed metal compounds such as NaAlF_6 or KAlF_6 may also be used.

Proportions of the alkali metal halide and the tungsten compound are not critical, provided the amount of halide is sufficient for ready formation of a homogenous melt for treatment with the hydrocarbon gas. The percent of tungsten (in percent WO_3 by weight) will generally range from about 5 to 30. Formation of the melt is accomplished by simply heating an admixture of halide and tungsten compound to a temperature and for a time sufficient to form a melt of sufficient fluidity for sparg-

EXAMPLE 2

Feed material - California scheelite concentrate	
Analysis, pct	
WO ₃ CaO Fe ₂ O ₃	
69.3 18.1 2.6	
High Temperature phase separation	
Charge	grams
Scheelite	432
NaCl	420
NaF	201
Al ₂ O ₃	72
Al ₂ SiO ₅	366
	1,491

The phase separation was made with the same procedure as that of Example 1.

The molten phases were decanted into separate slag pots.

Analysis of the phases, pct			
	Wt. g	WO ₃	CaO
Halide	909	31.5	0.22
Silicate	515	2.0	14.5
	1,424		

Gas Sparging of Halide Phase

The halide phase containing 96 pct of the WO₃ from the scheelite was treated by natural gas sparging. The natural gas contained, in pct: methane, 93.63; carbon dioxide, 0.70; nitrogen, 0.47; ethane, 3.58; propane, 1.02; other hydrocarbons, 0.60.

A 600-gram charge was melted at 1,100° C. in a 3" I.D. × 7" high graphite crucible. A ¼" O.D. × ¼" I.D. Alundum tube was used for gas sparging the melt. Natural gas was passed through the melt for 6 hours at a rate of 4 liters/min STP. The tube was removed and the remaining molten salt in the crucible was decanted into a slag pot. The WC was recovered from the cooled crucible by water leaching and scraping. The WC product was leached in dilute HCl and NaOH solutions, and treated for free carbon removal in heavy liquids.

Results										
WC recovered = 120 g										
W recovered as WC, pct = 75										
Final melt, g = 360										
Final melt, pct WO ₃ = 9.5										
Final melt, g WO ₃ = 34.0										
x-ray Diffraction of WC product										
Major WC										
Spectrographic analysis of WC product, pct										
Al	Cu	Fe	Mg	Mn	Mo	Si	Sn	Ti	V	
0.005	0.007	0.1	0.005	0.05	0.001	0.05	0.003	0.005	<.006	
Other impurities below detection limits.										
Carbon and oxygen analysis, pct										
C = 6.31										
O = 0.32										

EXAMPLE 3

Gas Sparging of Halide Phase Prepared from Wolframite in a Metal Alloy Crucible

A 1,600 gram charge of halide phase prepared according to the procedure of Example 1, and containing 25 wt pct WO₃, was melted in an Inconel 600 crucible

3" I.D. × 12" high. A ¼" Inconel pipe was the sparging tube. The melt was heated to 1,070° C. and methane sparged for 4 hours at a gas flow rate of 5 liters per minute STP. The WC was recovered by decanting off the unreacted melt, cooling the crucible and water leaching and scraping. The WC product was leached in dilute HCl and NaOH solutions, water washed and dried.

Results										
WC recovered = 181.5 g										
W recovered as WC, pct = 54										
Final melt, g = 992										
Final melt, pct WO ₃ = 15.5										
Final melt, g WO ₃ = 153.8										
X-Ray Diffraction										
Major WC										
Spectrographic analysis of WC product, pct										
Al	Ca	Cr	Cu	Fe	Mg	Mn	Mo	Na	Ni	Si
0.005	<.01	0.1	0.002	0.4	0.001	0.001	0.05	0.4	0.02	0.02
Other impurities below detection limits.										
Carbon and oxygen analysis, pct										
C = 6.19										
O = 0.07										

The Inconel crucible was used a total of 5 times with similar results. A major advantage of using the Inconel crucible was that free carbon was not detected in the WC product, thus eliminating a free carbon cleaning step.

EXAMPLE 4

WC from Na ₂ WO ₄	
Charge	grams
NaCl	440
Na ₂ WO ₄	160
	600

Procedure

The charge was melted in an alumina ceramic crucible 2½" I.D. × 6" high, at 1,100° C. Methane gas was passed through the melt for 6 hours at a flow rate of 4 liters/min STP.

Results										
WC recovered = 92 g										
W recovered as WC, pct = 86										
Final melt, g = 260										
Final melt, pct WO ₃ = 6.2										
Final melt, g WO ₃ = 16										
Spectrographic analysis of WC product, pct										
Al	B	Cu	Fe	Mg	Mn	Na	Pb	Si	Sn	Ti
0.05	0.004	0.01	0.03	0.02	0.02	0.4	<.01	0.1	<.002	0.01

WC was also prepared in NaCl-Na₂WO₄ melts containing 50 pct WO₃. The WC yield was about 50 pct.

EXAMPLE 5

WC from WO ₃	
Charge	grams
NaCl	500
WO ₃	100
Na ₂ CO ₃	46
	646

-continued

WC from WO ₃	
Charge	grams
<u>Procedure:</u>	
Temperature, 1,100° C.	
Graphite crucible, 3" I.D. × 7" high	
¼" alumina sparging tube	
Methane gas sparged for 6 hours at a flow rate of 3 liters/min STP	
<u>Results</u>	
WC recovered = 68 g	
W recovered as WC, pct = 80	
Final melt, g = 398	
Final melt, pct WO ₃ = 5.0	
Final melt, g WO ₃ = 19.9	

The analyses were similar to those obtained in Example 4.

EXAMPLE 6

WC from ammonium paratungstate (89 pct WO ₃)	
Charge	grams
NaCl	500
APT	140
NaOH	43
	683

Procedure

The charge was melted in a 3" I.D. × 7" high graphite crucible at 1,100° C. Methane gas was passed through a ¼" alumina tube into the melt for 6 hours at a flow rate of 4 liters/min STP. Ammonia gas was given off during heating of the APT prior to melting.

Results:	
WC recovered = 74 g	
W recovered as WC, pct = 70	
Final melt, g = 307	
Final melt, pct WO ₃ = 7.5	
Final melt, g WO ₃ = 23.0	

The analyses were similar to those obtained in Example 4.

We claim:

1. A process for preparation of tungsten monocarbide comprising:
 - (a) providing a molten composition comprising an alkali metal halide and an oxygen compound of tungsten;
 - (b) sparging said composition with a gas comprising a gaseous hydrocarbon which is selected from the group consisting of natural gas, methane, ethane, acetylene, propane, butane, mixtures thereof, and admixtures of these gases with H₂ or CO, at a temperature of about 900° to 1100° C. for a sufficient time for the tungsten compound to be substantially converted to tungsten carbide; and
 - (c) decanting the molten halide from the tungsten carbide product.
2. The process of claim 1 wherein the alkali metal halide is sodium chloride.
3. The process of claim 1 in which the oxygen compound of tungsten is tungstic oxide, an alkali metal tungstate, or ammonium tungstate.
4. The process of claim 3 in which the tungsten compound is sodium tungstate.
5. The process of claim 1 in which the gaseous hydrocarbon is methane or natural gas.
6. The process of claim 1 in which the tungsten carbide product is cooled and purified by water leaching.
7. The process of claim 1 in which the molten composition consists essentially of a mixture of sodium chloride and sodium tungstate.
8. The process of claim 7 in which the NaCl-Na₂WO₄ mixture is prepared by forming a melt comprising a tungsten ore concentrate, sodium chloride and sodium silicate, whereby the tungsten concentrates in the sodium chloride phase.
9. The process of claim 8 in which the tungsten ore is scheelite or wolframite.
10. The process of claim 1, wherein a reductant is included in the molten composition.
11. The process of claim 10, wherein the reductant is selected from the group consisting of powdered charcoal, coke breeze and calcium carbide.

* * * * *